

### IN THE CLAIMS

This listing of claims replaces all prior listings:

1. (Cancelled)

2. (Cancelled)

3. (Currently Amended) ~~A semiconductor light emitting device as set forth in claim 2;~~

A semiconductor light emitting device, comprising:

a substrate;

a first conductive type first cladding layer on said substrate;

an active layer on said first cladding layer; and

a second conductive type second cladding layer on said active layer, a part thereof having a ridge-shaped portion as a current narrowing structure,

wherein,

said first ridge-shaped layer and said second ridge-shaped layer are a layer with a relatively high aluminum composition ratio and a layer with a relatively low aluminum composition ratio, respectively,

said ridge-shaped portion of said second cladding layer includes a first ridge-shaped layer on the side closest to said active layer and having a relatively high bandgap and a second ridge-shaped layer on the side distant from the active layer and having a relatively low bandgap,

an aluminum composition ratio X1 of said first ridge-shaped layer is  $0.60 \leq X1 \leq 0.70$ , and

an aluminum composition ratio X2 of said second ridge-shaped layer is  $X2 \leq X1$ .

4. (Currently Amended) A semiconductor light emitting device as set forth in claim [[2]]  
3, wherein;

an aluminum composition ratio X1 of said first ridge-shaped layer is 0.70, and  
an aluminum composition ratio X2 of said second ridge-shaped layer is 0.65.

5. (Currently Amended) A semiconductor light emitting device as set forth in claim [[1]]  
3, wherein a film thickness of said first ridge shaped layer is 50 to 400 nm.

6. (Currently Amended) A semiconductor light emitting device as set forth in claim [[1]]  
3, wherein a sum of a film thickness of a portion excepting said ridge-shaped portion of said  
second cladding layer and a film thickness of said first ridge-shaped layer is 750 nm or smaller.

7. (Currently Amended) A semiconductor light emitting device as set forth in claim [[1]]  
3, wherein an etching stop layer is [[formed]] on a boundary face of a portion excepting the  
ridge-shaped portion of said second cladding layer and said first ridge-shaped layer.

8. (Currently Amended) A semiconductor light emitting device as set forth in claim [[1]]  
3, wherein said first cladding layer, said active layer and said second cladding layer ~~are formed~~  
by comprises an AlGaInP-based material.

9. (Currently Amended) A semiconductor light emitting device as set forth in claim [[1]]  
3, wherein said first cladding layer, said active layer and said second cladding layer ~~are formed~~  
by comprises an AlGaN-based material.

10. (Original) A semiconductor light emitting device as set forth in claim [[1]] 3,  
wherein said first ridge-shaped layer ~~is formed by~~ comprises a layer having an equal refractive  
index to that of a portion excepting said ridge-shaped portion of said second cladding layer.

11. (Currently Amended) A semiconductor light emitting device as set forth in claim  
[[1]] 3, wherein said first ridge-shaped layer ~~is formed by~~ comprises a layer having a lower

refractive index than that of a portion excepting said ridge-shaped portion of said second cladding layer.

12. (Currently Amended) A semiconductor light emitting device as set forth in claim 11, wherein an aluminum composition ratio of said portion excepting said ridge-shaped portion of said second cladding layer is 0.68, and an aluminum composition ratio of said first ridge-shaped layer is 0.75 to 0.80.

13. (Cancelled)

14. (Cancelled)

15. (Currently Amended) ~~A method of producing a semiconductor light emitting device as set forth in claim 14, wherein~~

A method of producing a semiconductor light emitting device, including:

a step of forming at least a first conductive type first cladding layer, an active layer and a second-conductive type second cladding layer by stacking on a substrate by an epitaxial growth method; and

a step of processing a ridge-shaped portion as a current narrowing structure at a part of said second cladding layer[;],

wherein,

in the step of forming said second cladding layer, a ridge-shaped portion is formed to include a first ridge-shaped layer on the side close to said active layer and having a relatively high bandgap and a second ridge-shaped layer on the side distant from the active layer and having a relatively low bandgap,

in the step of forming said second cladding layer, a layer having a relatively high aluminum composition ratio and a layer having a relatively low aluminum composition ratio are formed as said first ridge-shaped layer and said second ridgeshaped layer, respectively, and

in the step of forming said second cladding layer, a layer having an aluminum composition ratio  $X1$  satisfying  $0.60 \leq X1 \leq 0.70$  is formed as said first ridge-shaped layer and a layer having an aluminum composition ratio  $X2$  of  $X2 \leq X1$  as said second ridge-shaped layer.

16. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim [[14]] 15, wherein in the step of forming said second cladding layer, a layer having an aluminum composition ratio  $X1$  of 0.70 is formed as said first ridge-shaped layer and a layer having an aluminum composition ratio  $X2$  of 0.65 is formed as said second ridge-shaped layer.

17. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim [[14]] 15, wherein in the step of forming said second cladding layer, said first ridge-shaped layer is formed to have a film thickness of 50 to 400 nm.

18. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim [[14]] 15, wherein in the step of forming said second cladding layer, a sum of a film thickness of a portion excepting said ridge-shaped portion of said second cladding layer and a film thickness of said first ridge-shaped layer is made to be 750 nm or smaller.

19. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim [[14]] 15, wherein in the step of forming said second cladding layer, an etching stop layer is formed on a boundary face of a portion excepting said ridge-shaped portion of said second cladding layer and said first ridge-shaped layer.

20. (Currently Amended) A The method of producing a semiconductor light-emitting device as set forth in claim 19, wherein in the step of processing said ridge-shaped portion as the current narrowing structure at the part of said second cladding layer, the part of said second cladding layer is processed to be said ridge-shaped portion by etching which stops at said etching stop layer.

21. (Currently Amended) A The method of producing a semiconductor light-emitting device as set forth in claim [[13]] 15, wherein said first cladding layer, said active layer and said second cladding layer are formed by ~~an~~ of AlGaInP-based material.

22. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim [[13]] 15, wherein said first cladding layer, said active layer and said second cladding layer are formed by ~~an~~ of AlGaIn-based material.

23. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim [[13]] 15, wherein in the step of forming said second cladding layer, a layer having a same refractive index as that of a portion excepting said ridge-shaped portion of said second cladding layer is formed as said first ridge shaped layer.

24. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim [[13]] 15, wherein in the step of forming said second cladding layer, a layer having a lower refractive index than that of a portion excepting said ridge-shaped portion of said second cladding layer is formed as said first ridge shaped layer.

25. (Currently Amended) A The method of producing a semiconductor light emitting device as set forth in claim 24, wherein in the step of forming said second cladding layer, a layer having an aluminum composition ratio of 0.68 is formed as a portion excepting said ridge-shaped

portion of said second cladding layer and a layer having an aluminum composition ratio of 0.75 to 0.80 is formed as said first ridge-shaped layer.